

# Gyproc Ready Mix Joint Cement

## Product data sheet

### Introduction

#### Overview

Gyproc Ready Mix Joint Cement is a ready mixed air-drying jointing material for all stages of plasterboard jointing.

#### Applications

Gyproc Ready Mix Joint Cement can be used for all stages of hand or mechanical jointing of plasterboard and Glasroc specialist boards.

### Standards

Gyproc Ready Mix Joint Cement complies with *EN 13963 type 3A*, and is manufactured under a quality system independently audited and certified as conforming with *ISO 9001: 2000*.

### Performance

#### Fire resistance

Most fire-rated British Gypsum systems require the board joints to be filled, either with Gyproc jointing materials or Thistle finish plasters, even in locations where the system is not visible to building users, in order to achieve the tested performance. Gyproc Ready Mix Joint Cement is suitable for this purpose.

#### Effect of temperature

Ambient and background temperature must be maintained above 2°C until fully dry. Unused product in tubs must be protected from freezing. The Gyproc plasterboard background only is suitable for situations where the temperature does not exceed 49°C.

#### Effect of condensation and other moisture

Gyproc Ready Mix Joint Cement should be protected from continuous exposure to moisture. Prolonged or repeated exposure to moisture may cause a loss of strength and/or adhesion.

### Coverage

Jointing system	Reinforcement	Taping coat kg/100 lm	First finish coat kg/100 lm	Second finish coat kg/100 lm	Third finish coat kg/100 lm
Flat joint (tapered edge - hand applied)	Paper tape / fibre tape	12 (JF)	6 (JC)	6 (JC)	–
		12 (JF)	6 (JF)	6 (JC)	–
		12 (JC)	6 (JC)	6 (JC)	–
		9 (EF)	5 (EF)	–	–
Flat joint (tapered edge - mechanical)	Paper tape	6 (JC)	6 (JC)	6 (JC)	3 (JC)
Flat joint (square edge)	Paper tape	3 (JC)	12 (JC)	–	–
External angle	Corner tape	22 (JF)	9 (JC)	9 (JC)	–
		22 (JF)	9 (JF)	9 (JC)	–
		18 (EF)	9 (EF)	–	–
External angle	Metal bead	34 (JF)	9 (JC)	9 (JC)	–
		34 (JF)	9 (JF)	9 (JC)	–
		28 (EF)	12 (EF)	–	–
Internal angle	Paper tape	12 (JF)	8 (JC)	8 (JC)	–
		12 (JF)	8 (JF)	8 (JC)	–
		12 (JC)	8 (JC)	8 (JC)	–
		10 (EF)	5 (EF)	–	–

#### Notes to table

**JF** - Gyproc Joint Filler    **JC** - Gyproc Joint Cement    **EF** - Gyproc Easi-Fill / Gyproc Easi-Fill 45

1. These quantities should be used as a guide only – quantities used will vary depending on tools used and accuracy of board alignment.
2. Material used for pre-filling gaps, repairing damage, screw-spotting etc is not included.
3. When using a ready mix joint cement in place of powder, assume 1 litre is equivalent to 0.85kg of powder joint cement.
4. An allowance for waste and material sanded away should be added as appropriate.
5. External angle reinforcements should be fixed using a setting product – Gyproc Joint Filler or Gyproc Easi-Fill / Gyproc Easi-Fill 45, except Glasroc MultiBoard and Glasroc FireCase s.

## Performance (continued)

### Water requirement

See Installation - 'Mixing', later.

### Minimum temperature

Ambient and background temperature must be maintained above 2°C until fully dry.

### Pallet quantity

64 x 12 litre tubs, weighing approx 1280kg.

## Installation

### Background preparation

Plasterboard surfaces should be reasonably dry, clean and protected from the weather. Boards should be securely fixed with no steps between adjacent boards. The correct fixings must be used and properly located with their heads just below the liner surface. Any protruding screw heads should be driven home with a hand screwdriver, prior to spotting and jointing. Gaps between boards greater than 3mm should be pre-filled using Gyproc Joint Filler, Gyproc Easi-Fill or Gyproc Easi-Fill 45 prior to taping with Gyproc Joint Tape.

### Storage

Pallets of tubs should not have other materials stacked on top. The product should be maintained between 5°C and 30°C. Tubs are marked with the 'use by:' date in order to permit use in strict rotation.

### Mixing

Open the tub lifting the lip of the lid all the way round then lifting off. Stir before use, then dilute only if necessary and using no more than 0.75 litre per tub. Excessive dilution increases shrinkage and drying times, and reduces strength. Excessive mechanical mixing should be avoided, and only low-speed mixers used. Once opened, material may be stored in the tub and used over a week, if protected from drying out or contamination by other materials.

### Application

If using Gyproc Ready Mix Joint Cement for all stages, apply to the joint to embed the tape and immediately overcoat to fully fill the tapered board edges. Allow to completely dry, then apply a second coat, feathered out beyond the first. Allow to completely dry, then apply a final coat, feathered out beyond the second. If using as the finishing coat(s) over Gyproc Joint Filler the procedure is similar except that the Gyproc Joint Filler can be overcoated when it has set but not dried. Procedures for finishing angle joints, screw spotting etc are similar – please refer to the British Gypsum SITE BOOK for full details.

### Finishing

After the finishing coat has dried, sand lightly to remove trowel marks etc. Apply Gyproc Drywall Primer to the whole surface to prepare the surface for painting, or Gyproc Drywall Sealer in one coat to prepare for wallpapering or two coats to provide a vapour check.

### Decoration

Apply decoration with the minimum of delay after Gyproc Drywall Primer or Gyproc Drywall Sealer has dried. Note that, as with all wall and ceiling areas, gloss or high-sheen finishes will highlight any variations of the surface, particularly with shallow-angle lighting. The use of low-sheen or matt finishes minimises this risk. Jointing should be carried out under similar lighting conditions to those used for subsequent inspection and use.

Heavy, semi-rigid or impermeable wallcoverings may involve specialist adhesives or techniques which may not be compatible with Gyproc Drywall Primer or Gyproc Drywall Sealer. Consult the wallcovering and/or adhesive manufacturer for a specific recommendation. Impermeable wallcoverings fixed with water-based adhesives should not be applied over Gyproc Drywall Sealer, as the drying of the adhesive will be severely restricted.

### Maintenance

If the product is correctly applied and not exposed to moisture or mechanical damage, it should not require any form of maintenance.

# Gyproc Ready Mix Joint Cement

## Product data sheet

### Health & Safety

#### 1. Identification of the substances / preparation and company

##### Gyproc Ready Mix Joint Cement

Supplier British Gypsum Limited  
East Leake  
Loughborough  
Leicestershire  
LE12 6HX

Telephone 08705 456123

Recommended uses: Jointing material for plasterboards and Glasroc specialist boards.

#### 2. Composition / information on ingredients

General Composition: Gyproc Ready Mix Joint Cement is limestone and mica based, with small amounts of vinyl polymers and workability aids. It is water-based.

#### 3. Hazards identification

THE MOST IMPORTANT HAZARDS ARE:

This product is not classified as dangerous according to CHIP.

Dust from sawing or sanding may irritate the respiratory system, skin and eyes.

#### 4. First aid measures

Eye contact Wash eyes with clean water.

Skin contact Wash thoroughly with soap and water.

Ingestion DO NOT INDUCE VOMITING. Rinse out mouth thoroughly and give plenty of water.

Inhalation If irritation occurs, remove person to fresh air.

General Get medical attention if any symptoms persist.

#### 5. Fire fighting measures

The product does not pose a fire hazard. However, packaging materials may burn.

Suitable extinguishing media – water, foam, carbon dioxide or dry powder.

#### 6. Accidental release measures

Avoid creating dust – see Section 8 Exposure control/ personal protection for recommended personal protective equipment.

Product can be mixed with water, avoid eye contact or prolonged, repeated contact with skin – see Section 3 Hazards identification.

Prevent products from contaminating drains.

#### 7. Handling and storage

Use – Avoid eye contact or prolonged or repeated contact with skin – see Section 8 Exposure control/ personal protection and Section 3 Hazards identification.

Manual handling – Supplied in tubs of nominal 12 litre capacity, weighing approximately 20kg – use appropriate lifting technique.

Mechanical handling – In order to maintain the stability of the palletised load, it is important that the lift truck fork length and centres are set to correctly support the load.

Storage – Store in dry frost-free conditions. To maintain stability, place pallets on firm level ground. Do not stack more than one lift high.

#### 8. Exposure control / personal protection

##### Workplace exposure limit

Substance	Total inhalable	Respirable
Limestone	10mg/m <sup>3</sup> (8hr TWA)	4mg/m <sup>3</sup> 8hr TWA

##### Personal protection

Respiratory Use in a well ventilated area. Where practicable use engineering methods to control dust levels. If the exposure standards could be exceeded use a disposable face mask complying with EN 149 FFP2

Skin Wear appropriate clothing to protect against repeated or prolonged skin contact.

Eye If there is a risk of material entering the eye, wear eye protection to BS EN 166

**Health & Safety (continued)****9. Physical and chemical properties**

Appearance Aqueous dispersion

Odour None

pH 7 - 9

**10. Stability and reactivity**

No special physical conditions need to be avoided. No specific restrictions regarding incompatible materials.

**11. Toxicology information**

Inhalation Dust may irritate the respirable system. No known long term effects.

Skin contact Wet product may form an alkaline solution and irritate the skin. Dry powder can cause irritation.

Eye contact Wet product may form an alkaline solution and irritate the eye. Dry powder can cause irritation.

Ingestion Small quantities of product should not cause any significant reaction or long term effect.

**12. Ecological information**

Not applicable.

**13. Disposal consideration**

Classified as 'non-hazardous' but should not be co-disposed with municipal waste. Dispose at an authorised landfill site in accordance with the Waste Management Licensing Regulations (see Section 16 – Other information).

**14. Transport information**

Not classified as hazardous for transportation.

**15. Regulatory information**

Not classified under the CHIP regulations.

**16. Other information**

Control of Substances Hazardous to Health Regulations  
The Manual Handling Operations Regulations  
HSE Guidance Note EH40: Workplace Exposure Limits  
The British Gypsum WHITE BOOK  
The British Gypsum SITE BOOK

**Note to User:**

This Product Data Sheet does not constitute a workplace risk assessment for COSHH.

There are a number of situations where the approach to manual handling of British Gypsum products should be considered. For further guidance, please refer to the Manual Handling Section of the SITE BOOK, available to download from [www.british-gypsum.com](http://www.british-gypsum.com)

Date of previous version: First edition.

Gyproc, Thistle, Gypframe, Glasroc and Arteco are all registered trade names of BPB United Kingdom Limited. Isover is a registered trade name of Saint-Gobain.

British Gypsum reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation.

For a comprehensive and up-to-date library of information visit the British Gypsum website at: [www.british-gypsum.com](http://www.british-gypsum.com)

Telephone: 08705 456123

Fax: 08705 456356

E-mail: [bgtechnical.enquiries@bpb.com](mailto:bgtechnical.enquiries@bpb.com)

Training enquiries: 08702 406040



FM 52358

© British Gypsum January 2008 DS-116-01